


TECHNICAL FEATURES

MODEL: AT.MURANO MARFIL
SIZE: 60x120(F)
THICKNESS(mm): 9
DATE: 24/06/2024
CODE: 017.250.0033.06550
GROUP: GROUP B1b UNE-EN 14411 Annex H / SASO ISO 13006:2018 Annex H
TILE TYPE: GL
FINISH: RECTIFIED GLOSS
FAMILY: GLAZED PORCELAIN TILES
NUMBER OF DESIGNS:



TEST	RESULT	
UNE-EN ISO 10545-2 DIMENSIONAL FEATURES	COMPLIES WITH THE STANDARD	
UNE-EN ISO 10545-3 WATER ABSORPTION	0,5 % - 3 %	
UNE-EN ISO 10545-4 MODULUS OF RUPTURE - BREAKING STRENGTH	1600-2400 N	
	MODULUS OF RUPTURE - BENDING STRENGTH	30-40 N/mm2
UNE-EN ISO 10545-7 RESISTANCE TO SURFACE ABRASION	PEI IV	
UNE-EN ISO 10545-8 LINEAR THERMAL EXPANSION	<7,0 x 10⁻⁶ °C⁻¹	
UNE-EN ISO 10545-9 THERMAL SHOCK RESISTANCE	RESISTS	
UNE-EN ISO 10545-11 CRAZING RESISTANCE	RESISTS	
UNE-EN ISO 10545-12 FROST RESISTANCE	RESISTS	
UNE-EN ISO 10545-13	CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L	A
	CHEMICAL RESISTANCE - SODIUM HYPOCHLORITE 20 MG/L	A
	CHEMICAL RESISTANCE - HYDROCHLORIC ACID 3%	COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - CITRIC ACID 100 G/L	COMPLIES WITH THE STANDARD
	CHEMICAL RESISTANCE - POTASSIUM HYDROXYDE 30 G/L	COMPLIES WITH THE STANDARD
UNE-EN ISO 10545-14	STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL	5
	STAIN RESISTANCE - IODINE SOLUTION IN ALCOHOL	5
	STAIN RESISTANCE - OLIVE OIL	5

SLIP RESISTANCE

	TEST		RESULT
	UNE 41901:2017 EX	SLIP RESISTANCE (PENDULUM)	-
	DIN 51130	CRITICAL ANGLE OF SLIP (INCLINED PLATFORM)	-
	DIN 51097	CRITICAL ANGLE OF SLIP. WET-LOADED BAREFOOT AREAS	-
	BS7976 (PTV) WET	CLASSIFICATION ACCORDING TO PENDULUM TEST VALUES (PTV) WET	-
	ANSI A326.3	DYNAMIC COEFFICIENT OF FRICTION (DCOF) OF RIGID FLOORS.	-

TEST		VALOR UPEC
UPEC	UPEC CERTIFICATION	-

Declaration of Performance:

https://www.pamesa.com/ERP/4.0/empresas/151/045/ficheros/t00030006/114/DdP_DoP_N004CPR2013.pdf

TECHNICAL DEPARTMENT
PAMESA CERÁMICA